



# BEMAC LABORATORIES

Subsidiary of Mahaffey Associates Pty Ltd A.C.N. 001 629 036  
4 Mary Parade Rydalmere NSW 2116  
PO Box 349 Rydalmere NSW 2116  
Telephone: (02) 9684 2422 Fax: (02) 9684 2310

BJC/BJC/L22/L01/6047

11<sup>th</sup> May, 1998.

Dry-Treat (Australia) Pty Ltd  
PO Box 551  
ST LEONARDS NSW 2065

Attention: Luke

Dear Sir,

Re: Resistance to Salt Attack Tests on Pavers.

We have now completed the above testing on pavers supplied by you to AS/NZS 4456.10. The results are shown below.

Test Method: Method A of AS/NZS 4456.10.

Date Tested: 3<sup>rd</sup> April, 1998 – 4<sup>th</sup> May, 1998.

<i>Sample</i>	<i>Percentage Mass Loss After 15<sup>th</sup> Cycle (Ave)</i>	<i>Category</i>
Sandstone 1 – Control	3.56	General purpose
Sandstone 1 – Treated DT40SK	0.00	Exposure
Sandstone 1 – Treated STAIN-PROOF	0.00	Exposure
Sandstone 2 – Control	3.45	General purpose
Sandstone 2 – Treated STAIN-PROOF	0.00	Exposure

Note: Sandstone 1 and Sandstone 2 – Damage: Rounding of Corners.

Please do not hesitate to contact us should you require any further assistance.

Yours sincerely,

*B. Cockle*

Bronwen Cockle  
Laboratory Manager