

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : MJS Floorcoverings
PO Box 2393
Brisbane QLD 4122

Test Number : 22-002092
Issue Date : 8/08/2022
Print Date : 10/08/2022

Sample Description Clients Ref : "C L 9140 Cush'N'Lay Underlay"
Underlay tested under Centauri woven axminster cut pile carpet
Nominal Composition : Carpet: 80% Wool, 20% Nylon
Nominal Mass per Unit Area/Density : Foam: 140kg/m³ Carpet: 1929g/m²
Nominal Thickness : Foam: 9mm Carpet: 9.7mm



274899

58735

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : MJS Floorcoverings
PO Box 2393
Brisbane QLD 4122

Test Number : 22-002092
Issue Date : 8/08/2022
Print Date : 10/08/2022

AS ISO 9239.1-2003

Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 09-06-2022

Date Tested 08-08-2022

CHF Value	1	2	3	Mean
Length	8.1	-	-	- kW/m ²
Width	7.9	8.1	7.0	7.7 kW/m ²

Smoke Value	1	2	3	Mean
Length	78	-	-	- % .min
Width	112	72	95	93 % .min

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

Each specimen was adhered to Dunlop - Carpet cushion underlay using RLA - R656 adhesive and then bonded to 6mm thick fibre reinforced cement board using RLA - R656 adhesive and clamped prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

dual bond on CL9140 CUSH N LAY underlay

274899

58735

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR