



PRODUCT DATA SHEET

For use on all types of ball bearings

PHYSICAL CHARACTERISTICS

Color	Blue Green	Volume Solids	>92%
Appearance	Clear	Film Thickness	0.0004" typical
Odor	Fresh Scent	pH	N/A
Specific Gravity @ 15.6°C	0.895	Vapor Pressure	8 mm Hg
Viscosity, cSt @ 40°C	33.0	Solubility in Water	Slightly Emulsifiable
cSt @ 100°C	7.0	Boiling Point	>200°C
Flash Point c.o.c.	>132°F	Weight per gallon	7.46 lbs.

PERFORMANCE PROPERTIES

Lubrication:	Anti-Wear	0.242 mm**	ASTM D4172
	Friction Coefficient	0.044	
	Load Carrying Capacity	750 lbs.	ASTM 2625 Method B
Corrosion Protection:	Salt Spry, hrs.	>96*	ASTM B117
	(Film Thickness)	0.19 mils	
	Humidity Cabinet, hrs.	1320	ASTM D1748

*Sand blasted mild steel panel. 0 - <1% surface rust

**Note: The smaller the number, the better the performance. A standard lubricating oil of the same viscosity would yield a value of 1.0 - 1.2 mm.

COMPATIBILITY

Greases and Oils: Compatible with other hydrocarbon-based lubricants. For ultimate performance, remove bearing grease or other lubricants prior to applying SpeedX.

Rubber: No visible effect on Nitrile / Buna-N, Viton® or Neoprene products. Slight swelling and/or softening of butyl rubber items.

Adhesives and Sealants: Usually no effect but some adhesives may soften and sealants with silicone may experience slight swelling. Recommend a small test sample prior to widespread application.

Painted Surfaces: Paints typically used on aircraft, automobiles and machinery are unaffected by SpeedX. Polishes and some wax coatings may soften by the application of *any* hydrocarbon product.

Plastics: SpeedX is compatible with most commonly encountered plastics such as: acrylic, polyester, nylon, vinyl, Delrin®, PTFE, Formica®, polyethylene and polypropylene. Should there be any question when other types of plastics are involved, it is suggested a small sample be tested.

Fabrics: SpeedX will be absorbed into the fibers of most fabrics, thereby creating slight staining. The stain is not permanent and may be removed with naphtha or mineral spirits.

Storage: Bulk: Store at room temperatures (50°F or more).

Shelf Life: Indefinite (as long as container remains capped).

*Registered trademark of E.I. DuPont de Nemours

** Registered trademark of Formica Corp