

CorrosionX Grease

Extreme-Performance • NLGI 2

Part Number 96801

<u>Test Property</u>	<u>Test Method</u>	
4-ball EP - Load Wear Index	ASTM D-2596	65
4 ball EP - Weld Point (kg)	ASTM D-2596	620
Rust Protection	ASTM D-1743	Pass
Water Washout @ 175oF (%)	ASTM D-1264	3
Mobility @ 0oF (g/min.)	USS DM 43	13.6
Mobility @ -20oF (g/min)	USS DM 43	4
N.L.G.I Grade	ASTM-D217	#2
Dropping Point (oF)	ASTM-D2265	550
Base Oil Viscosity @ 104oF/40oC (cSt)	ASTM D-445	220
Penetration @ 25oC - Unworked	ASTM D-217	265-295
Penetration @ 25oC - 60 strokes	ASTM D-217	265-295
Penetration @ 25oC - 100,000 strokes	ASTM D-217	265-295
Timken OK Load, lb.	ASTM D-2509	65
Thickener Type		Calcium Sulfonate Complex
Appearance	Visual	Smooth
Color	Visual	Green
Wheel Bearing Leakage (g)	ASTM D-1263	5 max
VOC (% by wt.)	ASTM-D-972	1
Specific Gravity @15oC		0.87
Flash Point (oF/oC)		400/204

U.S. Corrosion Technologies, LLC
2638 National Drive • Garland, TX 75041
Toll Free 800.638.7361 • Fax 972.278.9721
www.corrosionx.com
Made in the USA • © 2015 U.S. Corrosion Technologies, LLC • 1M507