



Tradies Choice – Master FS

Tradies Choice Master FS Additive

DESCRIPTION

Tradies Choice Master FS Liquid Accelerator can be mixed with cement based tile adhesives and sand and cement screeds to increase drying times.

SURFACE PREPARATION

The surface must be clean, dry firm and free of dust oil, grease, wax and curing compounds.

The substrate must be installed according to the relevant standards and manufacturer recommendations. All porous surfaces must be primed with SAS Master Primer. For non-porous surfaces such as existing tiles, adhesives must be primed using SAS Master Primer neat. Please contact SAS Technical Team for further information.



MIXING

Mix 300ml with 5.5-6L of water to have a set time of 3 hours @ 23°C allow longer times in cool conditions.

MOVEMENT JOINTS

Movement joints must be in accordance with Australian Standards AS 3958.1

PACKAGING

Master FS is available in 5L containers

Precautions

When tiling externally that is above 2.7m high please contact the SAS Technical team for further information.

Technical Data

Appearance – White liquid

SDS is available from www.sas-aa.com.au



SAS Australasia Pty Ltd
1300 202 894
www.sas-aa.com.au

ABN: 83 617 827 282

Disclaimer: The information supplied is to the best of SAS knowledge and is true and accurate. The application of the product is beyond SAS control and any alleged failure or damage must be inspected by a representative from SAS. All workmanship must be carried out in accordance with AS 3958.1-2007.