

VOC Emission Test Summary

Friday, 1st July 2011

Supplier: MJS Underlays Pty Ltd (32 Business St, Yatala, QLD, 4207)

Sample Description: Project 140 (P7140)

Date Tested: April 2011 (Tested by FORAY Laboratories – ISO 17025 Accredited)

Test Method: Carpet & Rug Institute Green Label test program incorporating ASTM D5116
“Standard Guide for Small-Scale Environmental Chamber Determinations of Organic Emissions from Indoor Material/Products”.

Emission Data:

Specification	Project 140 (P7140)
Green Building Council of Australia Green Star Office Design V2/V3 IEQ-13 Green Star Office Interiors V1.1 IEQ-11	
Total Volatile Organic Compound emission rate <0.5 mg/m ² /hr (24 hours)	Total Volatile Organic Compound emission rate 0.37 mg/m ² /hr (24 hours)
4-Phenylcyclohexene emission rate 0.05 mg/m ² /hr (24 hours)	4-Phenylcyclohexene emission rate <0.01 mg/m ² /hr (24 hours)
Formaldehyde Emission Rate <0.05 mg/m ² /hr (24 Hours)	Formaldehyde Emission Rate 0.01 mg/m ² /hr (24 Hours)



Dr. Vyt Garnys
PhD, BSc(Hons) AIMM, ARACI, ISIAQ
ACA, AIRAH, FMA
Managing Director and Principal Consultant

CV110419